

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
13 October 2005 (13.10.2005)

PCT

(10) International Publication Number
WO 2005/096319 A1

(51) International Patent Classification⁷: **H01B 1/10**

(21) International Application Number:
PCT/KR2005/000748

(22) International Filing Date: 15 March 2005 (15.03.2005)

(25) Filing Language: Korean

(26) Publication Language: English

(30) Priority Data:
10-2004-0022656 1 April 2004 (01.04.2004) KR

(71) Applicant (for all designated States except US): **DPI SOLUTIONS, INC.** [KR/KR]; #1601, Venture Incubating Center, Hanwha Chemical R & D Center, 6, Shinseong-dong, Yuseong-gu, Daejeon 305-345 (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LEE, Jong Woo** [KR/KR]; 276-32 Galhyeon 1-dong, Eunpyeong-gu, Seoul 122-804 (KR). **KIM, Chul Hwan** [KR/KR]; #101-1004 Gaenari APT., Tanbang-dong, Seo-gu, Daejeon 302-765 (KR). **YOON, Hyun Nam** [US/US]; 29 Woodshire Terrace, Towaco, NJ 07982 (US).

(74) Agents: **NAM, Hee Seob** et al.; Dabong Tower Bldg., 10th Fl., 890-12 Daechi-dong, Kangnam-gu, Seoul 135-280 (KR).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COMPOSITION FOR COATING ORGANIC ELECTRODE AND METHOD OF MANUFACTURING ORGANIC ELECTRODE HAVING EXCELLENT TRANSPARENCY USING THE COMPOSITION

(57) Abstract: The present invention relates to a composition for coating an organic electrode and method of manufacturing an organic electrode having a excellent transparency using the composition comprising 3% to 20% by weight of a polyhydric alcohol, polyol or a mixture thereof, 5% to 10% by weight of a primary alcohol having C1 to C5, 5% to 25% by weight of an amide, sulfide or a mixed solvent thereof, 0.01% to 0.1% by weight of a surfactant and an aqueous solution of polyethylenedioxythiophene (PEDOT) conductive polymers having nano-sized particle in a remainder. The present invention indicates the excellent transparency that transmittance of organic conductive layer is more than 90% in the visible ray area and sheet resistance is 300 to 900Ω/sq in case of coating. Therefore the present invention is capable of manufacturing the organic electrode such as an electrode or a writing material of organic transistor, smart card, antenna, electrode of battery and fuel battery, capacitor using for PCB, inductor, electromagnetic wave cover and a sensor etc. as well as the transparency electrode using for display.



WO 2005/096319 A1